



HAND PROTECTION

Keto-Handler Plus Solvent Resistant Unsupported Gloves with a Smooth Finish

DESCRIPTION

This extraordinary solvent-resistant glove features superior protection for handling some of the most difficult organic solvents including ketones, aromatic solvents, and chlorinated solvents. Designed with resistance toward high humid conditions, these unique gloves have an 11-mil thickness with blue PVA coated outside and nitrile inside. The finish is smooth and the glove is 13 inches in length.

Each pair is individually packaged in a polybag.

** PVA (Polyvinyl alcohol) is water-soluble and can break down easily in both water and alcohols. While the nitrile-coated interior provides an extra protection barrier, this glove is not recommended for use with alcohols, acids, bases, or chemicals containing a high percentage of water.



INDUSTRY

Organic Chemical Handling	Handling
Chlorinated Solvent Handling	Degreasing
Aromatic Solvent	Fuel Handling

ITEM 411 SIZES 7(S)-10(XL)

FEATURES

- PVA material provides resistance to ketones and organic solvents
- Nitrile material provides an extra protection barrier to both waters and alcohols
- Flexible 11 mil thickness provides excellent dexterity
- Straight cuff for extended forearm protection
- EN 388 Levels: 3001X

SPECIFICATIONS

COATING	COLOR	THICKNESS	LENGTH	COATING TYPE	FINISH	CUFF	EN 388 LEVELS
Nitrile/PVA	Blue	11 Mil	13 in.	Full	Smooth	Straight	3001X

PACKAGING

	QUANTITY	7(S)	8(M)	9(L)	10(XL)
PAIR UPC	1	NA	NA	NA	NA
INNER PACK UPC	12/PACK	816368029009	816368029016	816368029023	816368029030
CASE GTIN	12 PK/CASE	10816368029006	10816368029013	10816368029020	10816368029037
CASE WEIGHT (IN POUNDS)		22.3	23.6	25.6	27.8

PERMEATION DATA

EN ISO 374-01: 2016	CHEMICAL	PL	BTT
A	Methanol	2	42
B	Acetone	6	>480
C	Acetonitrile	6	>480
D	Dichloromethane	5	253
E	Carbon Disulfide	6	>480
F	Toluene	6	>480
G	Diethylamine	3	105
H	Tetrahydrofuran	5	408
I	Ethyl Acetate	6	>480
J	n-Heptane	6	>480
K	Sodium Hydroxide 40%	6	>480
L	Sulfuric Acid 96%	4	131
N	Acetic Acid 98%	5	336
P	Hydrogen Peroxide 30%	6	>480
S	Hydrofluoric Acid 40%	2	55

PERMEATION DATA WAS MEASURED IN TWO WAYS:
 1. FOR SOLVENTS – GAS CHROMATOGRAPHY
 2. FOR ACID AND BASES – BY CONDUCTIVITY MEASUREMENTS

* PL = Performance level
 * BTT = Break through time



Global Glove
 & Safety Manufacturing, Inc.

13915 Radium St NW
 Ramsey, MN 55303

763-450-0110
 Sales@GlobalGlove.com

GlobalGlove.com