

Pyrolon CRFR is the Chemical Resistant and Flame Resistant disposable option designed to protect your Primary FR and ARC Rated Garments when chemical splash is a concern. Pyrolon CRFR garments bar contaminating flammables like paint, oil and grease, hazardous liquids and contaminants, and dry particulates from penetrating to inner Primary Protective Garments, potentially saturating them with flammable substances.

Pyrolon CRFR is designed to be worn over Primary FR/AR Protective Clothing for environments where flash fire is a concern. Utilizing Pyrolon CRFR when both chemical splash and flash fire are a concern helps the wearer meet the NFPA 2113 requirements for section 5.1.9.

Pyrolon® CRFR Coveralls



Coverall 51100

- CollarStorm flap over zipper
- Open wrists
- Open ankles
- Hemmed cuff Sizes: S - 5XL Case Pack: 6



Coverall 51110

- CollarStorm flap over
- zipper
 Elastic wrists
- Elastic ankles Sizes: S - 5XL Case Pack: 6



Coverall 51130

- Hood
- Storm flap over zipper
- Elastic faceElastic wrists and
 - ankles Sizes: S - 5XL Case Pack: 6



Coverall 51150

- Hood
 Storm flap over
 zipper
- zipper

 Elastic face and
- wrists
 Attached boots
 Sizes: S 5XL
 Case Pack: 6



Coverall 51166

- Respirator fit hood
- Storm flap over zipper
- Elastic wrists
- Attached Boots
 Sizes: S 5XL
 Case Pack: 6

Pyrolon® CRFR Brand Features:

Combines Chemical Resistance with Flame Resistance

Does Not Melt or Drip

Meets the NFPA 2113
Requirements for Section 5.1.9

Penetration Data for ASTM F903 Standard Chemicals



Secondary FR and Chemical Protective Garment

Primary FR Protective Garment

Pyrolon® CRFR Configurations



Apron 51730

- Long sleeve
- Elastic wrists
- 32" length Sizes: S-4X Case Pack: 12



Jacket 51250

- Collar
- Elastic wrists
- Double storm flap

Case Pack: 6

 Hook and loop closure
 Sizes: S - 5XL

• Elastic ankles p Sizes: M-4X Case Pack: 6

Pant

51300 Pant

• Elastic waist



Boot Covers 51740P

- Elastic top
 - 17" high Sizes: One size Case Pack: 12 pair

Pyrolon® CRFR helps reduce Total Body Burn!

Pyrolon® CRFR third party testing by North Carolina State University to ASTM F1930 confirms:

Material	Body Burn Results
6.5 oz. Westex® DH alone	16.4% total body burn
Pyrolon® CRFR over 6.5 oz. Westex® DH	15.84% total body burn

Pyrolon® CRFR Physical Properties, 2.5 Mil

Physical Property	Test Method	Units	Test Results
Basis Weight		oz./sq. yd	4.92
Grab Tensile MD		lbs.	34
Grab Tensile XD		lbs.	27
Mullen Burst		lbs./sq.in.	35
Char Length MD		inches	4.7
Char Length XD		inches	4.5
Afterflame		seconds	<2
Charge Decay	NFPA 99		Pass
Surface Resistance	EN1149	Ω	Pass

Pyrolon® CRFR Penetration Data, 2.5 Mil, ASTM F903

Challenge Chemical	CAS Number	Physical State	Penetra- tion Result
Acetone	67-64-1	Liquid	>60
Acetonitrile	75-05-8	Liquid	>60
Benzene	71-43-2	Liquid	>60
Carbon Disulfide	75-15-0	Liquid	>60
Diesel Fuel	N/A	Liquid	>60
Diethylamine	109-89-7	Liquid	>60
Crude Oil	N/A	Liquid	>60
Ethyl Acetate	141-78-6	Liquid	>60
n-Hexane	110-54-3	Liquid	>60
Hexamethylene Diiso- cyanate	822-06-0	Liquid	>60
Hydrochloric Acid	7647-01-0	Liquid	>60
Methanol	67-56-1	Liquid	>60
Methyl Ethyl Ketone (MEK)	78-93-3	Liquid	> 60
Methyl Isobutyl Ketone	108-10-1	Liquid	>60
Monochlorobenzene	108-90-7	Liquid	>60
n-Butyl Acetate	123-86-4	Liquid	>60
Orthodichlorobenzene, Grade F	95-50-1	Liquid	>60
Polychlorinated Biphenyl (PCB)	92-52-4	Liquid	> 60
Sodium Hydroxide, 50%	1310-73-2	Liquid	>60
Sulfuric Acid, 98%	7664-93-9	Liquid	45
Surrogate Gasoline (Toulene 50%) (Isooctane 50%)	108-88-3 540-84-1	Liquid	> 60
Tetrachloroethylene	127-18-4	Liquid	>60
Toluene	108-88-3	Liquid	>60
Trichlorobenzene Mixture	Mixture	Liquid	>60
Xylene	1330-20-7	Liquid	>60

Note: Chemical Resistance Data is in accordance with ASTM F903 test method. Testing is performed on fabric samples only, not finished garments. Sources for all test data are independent laboratories. All tests were performed under laboratory conditions and not actual use conditions.